

CEWELD E DUR 71

TYPE	Basic coated electrode with a sintered tungsten carbide core wire.
ANWENDUNGEN	For extreme wear resistance, elements as Niobium and Chromium carbides are also added to obtain a complex carbide structure. Specially used for applications subject to abrasive wear such as sand or other minerals with little impact. Recommended for the brick and clay industry or extreme high temperature applications in power plant industries.
EIGENSCHAFTEN	CEWELD E DUR 71 is designed to offer full wear resistance and high hardness already achieved in the first layer. To be welded with low as possible current to avoid burnout of elements.
KLASSIFIKATION	
GEEIGNET FÜR	For extreme heavy abrasion and wear applications such as, mixers and screws in the brick and clay industry, electricity powerplant screws (ash), mining, drilling etc

ZULASSUNGEN

SCHWEISSPOSITIONEN



MECHANISCHE GÜTEWERTE

Heat Treatment	$R_{p0,2}$ (MPa)	R_m (MPa)	A5 (%)	Hardness
As Welded				65 HRc

RÜCKTROCKNUNG

Not required

HARDNESS HRC

first layer: $\pm 63-65$ HRc second layer: $\pm 66-70$ HRc

GAS ACC. EN ISO 14175

CEWELD E DUR 71

E DUR 71 3,2 X 350MM

Packaging	KG/unit	EanCode
Can	2,5	8720663402721

E DUR 71 4,0 X 350MM

Packaging	KG/unit	EanCode
Can	2,5	8720663402738