




CEWELD Alloy 33

TYPE	High-chromium austenitic alloy																									
ANWENDUNGEN	Typical applications of Alloy 33 include heat exchangers, condenser tubes and other equipment for the Refinery Industry and the Chemical Process Industry as well as light weight structures in the Offshore Industry. Especially the multi-purpose character of Alloy 33 with respect to its corrosion resistance as well to acidic and alkaline media as to chloride bearing cooling waters opens a wide variety of applications																									
EIGENSCHAFTEN	CEWELD Alloy 33 is a high-chromium austenitic Alloy. This alloy combines ease of fabrication with outstanding resistance to highly oxidizing media																									
KLASSIFIKATION	AWS EN ISO W.Nr. F-nr FM	A 5.9: ER33-31 14343-B: S Z 33 32 1 Cu N L 1.4591 6 6																								
GEEIGNET FÜR	1.4591, 1.4583 X 1CrNiMoCuN 33 32, X 1CrNiMoCuN 33 32 1, X 2 CrNiMo 18 10 Alloy 33, 1.4591																									
ZULASSUNGEN																										
SCHWEISSPOSITIONEN	    																									
TYPISCHE CHEMISCHE ANALYSE DES FÜLLMETALLS (%)	<table><tr><td>C</td><td>Si</td><td>Mn</td><td>Cr</td><td>Ni</td><td>Mo</td><td>N</td><td>Cu</td><td>Fe</td></tr><tr><td>0.01</td><td>0.3</td><td>1.5</td><td>33</td><td>32</td><td>1.5</td><td>0.5</td><td>1</td><td>Rem.</td></tr></table>								C	Si	Mn	Cr	Ni	Mo	N	Cu	Fe	0.01	0.3	1.5	33	32	1.5	0.5	1	Rem.
C	Si	Mn	Cr	Ni	Mo	N	Cu	Fe																		
0.01	0.3	1.5	33	32	1.5	0.5	1	Rem.																		
MECHANISCHE GÜTEWERTE	<table><tr><th rowspan="2">Heat Treatment</th><th rowspan="2">R_{P0,2} (MPa)</th><th rowspan="2">R_m (MPa)</th><th rowspan="2">A₅ (%)</th><th colspan="2">Impact Energy (J) ISO-V</th><th rowspan="2">Hardness</th></tr><tr><th>RT</th><th>-196°C</th></tr><tr><td>As Welded</td><td>450</td><td>920</td><td>42</td><td>100</td><td>32</td><td>HRc</td></tr></table>								Heat Treatment	R _{P0,2} (MPa)	R _m (MPa)	A ₅ (%)	Impact Energy (J) ISO-V		Hardness	RT	-196°C	As Welded	450	920	42	100	32	HRc		
Heat Treatment	R _{P0,2} (MPa)	R _m (MPa)	A ₅ (%)	Impact Energy (J) ISO-V		Hardness																				
				RT	-196°C																					
As Welded	450	920	42	100	32	HRc																				
RÜCKTROCKNUNG	Not required																									
GAS ACC. EN ISO 14175	I1																									



CEWELD Alloy 33

ALLOY 33 1,0MM

Packaging	KG/unit	EanCode
BS-300	15	8720663419767