



CEWELD 4829 MoTi

TYPE	Austenitic rutile stick electrode for welding Cr-Ni-Mo steels. (Type E 23 12 2 L R / E309LMo)								
APPLICATIONS	CEWELD® 4829 MoTi is for joining heat resistant CrNi-steels of the same kind and also joining dissimilar alloys such as steel to stainless steel. Cladding on low alloyed steels in case a 18/8/2 CrNiMo layer is required in the first layer.								
PROPERTIES	The increased ferrite content (FN~19) in the weld metal of CEWELD® 4829 MoTi enables high crack resistance with materials that are less suitable for welding. Particularly easy processing with very good seam appearance, both with direct and alternating current. Self-lifting slag. For application temperatures from -60°C to 300°C, for 1st layer weld claddings up to 400°C.								
CLASSIFICATION	AWS	A 5.4: E 309LMo-26							
	EN ISO	3581-A: E 23 12 2 L R 32							
	W.Nr.	1.4459							
	F-nr	1							
	FM	5							
SUITABLE FOR	23% Cr, 12%Ni, 3% Mo, 309LMo 1.4401, 1.4404, 1.4406, 1.4410, 1.4437, 1.4571, 1.4580, 1.4459, 1.4513, 1.4521, 1.4526, 1.4113, 1.4575 AISI 436, 444, 434 UNS S43600, S 44400, S43400,								
APPROVALS	CE								
WELDING POSITIONS	     								
TYPICAL CHEMICAL ANALYSIS OF WELD METAL (%)	C	Si	Mn	P	S	Cr	Ni	Mo	Fe
	0.02	0.7	1.8	0.02	0.015	24	13	2.5	Rem.
MECHANICAL PROPERTIES	Heat Treatment	R _{P0,2} (MPa)	R _m (MPa)	A ₅ (%)	Impact Energy (J) ISO-V			Hardness	
	As Welded	460	650	32	RT			HRc	
					55				
REDRYING	300°C / 2 hr								
GAS ACC. EN ISO 14175									



CEWELD 4829 MoTi

4829 MOTI 2,0 X 300MM

Packaging	KG/unit	EanCode
Can	2,4	8720663415707

4829 MOTI 2,5 X 300MM

Packaging	KG/unit	EanCode
Can	2,5	8720663415714

4829 MOTI 3,2 X 350MM

Packaging	KG/unit	EanCode
Can	2,8	8720663415721

4829 MOTI 4,0 X 350MM

Packaging	KG/unit	EanCode
Can	2,8	8720663415738

4829 MOTI 5,0 X 450MM

Packaging	KG/unit	EanCode
Can	3,0	8720663415745