



CEWELD 4576 Ti

TYPE	Rutile basic electrode for welding Cr-Ni-Mo steels with very low C-content										
APPLICATIONS	CEWELD® 4576 Ti is developed for welding Ti an Nb stabilized CrNi(N) and CrNiMo(N) types and cast steels (316Ti)										
PROPERTIES	CEWELD® 4576 Ti have excellent corrosion resistance as needed in chemical industry up to 400°C and exceptional weldability with no spatter and self lifting slag.										
CLASSIFICATION	AWS	A 5.4: E 318-16									
	EN ISO	3581-A: E 19 12 3 Nb R 12									
	W.Nr.	1.4576									
	F-nr	5									
	FM	5									
SUITABLE FOR	E 19 12 3 Nb R / E318-17 type 1.4301, 1.4404, 1.4435, 1.4581, 1.4437, 1.4401, 1.4541, 1.4550, 1.4571, 1.4473, 1.4580, 1.4583, 1.4436 G-X5CrNiMoNb 19 11 2, G-X6CrNiMo 18 12, X4CrNiMo 17 12 2, X6CrNiMoTi 17 12 2, X6CrNiMoNb 17 12 2, X10-CrNiMoNb 18 12, X3CrNiMo 17 13 3 AISI 316, 316Ti, 316Cb, 318 UNS S31600, S31603, S31635, S31640, S31653										
APPROVALS	CE										
WELDING POSITIONS	 PA  PB  PC  PD  PE  PF										
TYPICAL CHEMICAL ANALYSIS OF WELD METAL (%)	C	Si	Mn	P	S	Cr	Ni	Mo	Nb	Cu	Fe
	0.07	0.8	1.1	0.02	0.01	18	12	2.8	0.5	0.5	Rem.
MECHANICAL PROPERTIES	Heat Treatment	R _{P0,2} (MPa)	R _m (MPa)	A ₅ (%)	Impact Energy (J) ISO-V					Hardness	
	As Welded	440	600	30	RT					HRc	
REDRYING	300°C / 2 hr										
GAS ACC. EN ISO 14175											



CEWELD 4576 Ti

4576 Ti 2,0 X 300MM

Packaging	KG/unit	EanCode
Can	2,4	8720663411709

4576 Ti 2,5 X 300MM

Packaging	KG/unit	EanCode
Can	2,4	8720663411716

4576 Ti 3,2 X 350MM

Packaging	KG/unit	EanCode
Can	2,8	8720663411723

4576 Ti 4,0 X 350MM

Packaging	KG/unit	EanCode
Can	2,7	8720663411730