

CEWELD Nicro 602 CA Tig

TYPE Nickel based filler metal against extreme temperature conditions.

APPLICATIONS Welding similar alloys that have to resist extreme high temperature and for cladding steels or stainless steels to obtain a high temperature resistant surface against oxidation.

PROPERTIES Excellent welding properties with high build-up capacity and low dilution rate. Excellent resistance against temperature cycling conditions up to 1200°C and carburized medias. Excellent fatigue strength and creep properties.

CLASSIFICATION

AWS	A 5.14: ERNiCrFe-12
EN ISO	18274: S Ni 6025(NiCr25Fe10AlY)
W.Nr.	2.4649
F-nr	43
FM	6

SUITABLE FOR Cladding against high temperature, radiant heater tubes, furnace rolls, muffles in bright annealing furnaces (H2 atmosphere), rotary kilns, pipe hangers, waste gas components, hydrogen production, methanol and ammonia synthesis, 1.4767, 2.4633, 2.4649, NiCr25FeAlY, Nicrofer 6025 HT, Alloy 602CA, UNS N06025, Centralloy HTE

APPROVALS

WELDING POSITIONS



TYPICAL CHEMICAL ANALYSIS OF THE FILLER METAL (%)


C	Si	Mn	Cr	Ni	Ti	Fe	Al
0.2	0.4	0.4	25	65	0.15	10	2

MECHANICAL PROPERTIES

Heat Treatment	R _{P0.2} (MPa)	R _m (MPa)	A ₅ (%)	Impact Energy (J) ISO-V		Hardness
				RT		
As Welded	785	959	15	60		HRc

REDRYING Not required

GAS ACC. EN ISO 14175 I1



CEWELD Nicro 602 CA Tig

NICRO 602 CA TIG 1,6 X
1000MM

Packaging	KG/unit	EanCode
Tube	5	8720663418364

NICRO 602 CA TIG 2,0 X
1000MM

Packaging	KG/unit	EanCode
Tube	5	8720663418371

NICRO 602 CA TIG 2,4 X
1000MM

Packaging	KG/unit	EanCode
Tube	5	8720663418388