



CEWELD AA B550

TYPE	Basic seamless micro alloyed flux cored welding wire						
APPLICATIONS	Vessel and apparatus construction, offshore, lifting, drilling platforms etc.						
PROPERTIES	AA B550 is a seamless high basic flux cored wire for extreme requirements at sub zero temperatures down to -60 °C. Excellent welding properties. Yield strength > 550 MPa. Low hydrogen content HD< 3 ml/100g even after long storage.						
CLASSIFICATION	AWS	A 5.29: E80T5-K1M-J H4, A 5.36: E80T5-M21A4-K1-H4					
	EN ISO	18276-A: T 55 6 1NiMo B M21 1 H5					
	F-nr	6					
	FM	2					
SUITABLE FOR	Typical for: Reh ≤ 550 MPa ISO 15608: 1.2, 1.3, 2.1, 2.2, 3.1 1.8905 , 1.8907, 1.8937 , 1.8915, 1.8917, 1.8944 , 1.8954, 1.6780, 1.8817, 1.6368, 1.8807 15NiCuMoNb5, 17MnMoV53, WB36, 20MnMoNi4-5, WB35, BHW 35 , BHW 38, X42, X60, X80 StE 460, StE 500, WStE 500 , TStE 460, TStE 500, NAXTRA 56 , NAXTRA 63						
APPROVALS							
WELDING POSITIONS	  						
TYPICAL CHEMICAL ANALYSIS OF WELD METAL (%)	C	Si	Mn	P	S	Ni	Mo
	0.05	0.4	1.2	0.015	0.015	1	0.3
MECHANICAL PROPERTIES	Heat Treatment	R _{P0,2} (MPa)	R _m (MPa)	A ₅ (%)	Impact Energy (J) ISO-V		Hardness
					-60°C	-40°C	
	As Welded	580	720	20	80	100	
	570°C- 620°C 1h	680	550	25	65	50	HRc
REDRYING	Not required						
GAS ACC. EN ISO 14175	M21						