



CEWELD CuSi3 Tig

TYPE	Copper-Silicon welding wire for Tig welding				
APPLICATIONS	Welding thin plates and or galvanized plates in the car industry and also for cladding CuMn, CuSiMn and CuZn alloys. Suitable for cladding cast iron and un- and low alloyed steels. Examples: Automobile industry, art work, cladding on steel, cast iron and copper alloys etc.				
PROPERTIES	• High quality alloyed copper wire for the Tig process (Mig brazing as well) • The weld metal is a Copper- Silicon bronze • Sound, pore free deposits on ferrous and non-ferrous base materials • Excellent corrosion resistance				
CLASSIFICATION	AWS	A 5.7: ERCuSi-A			
	EN ISO	24373: Cu 6560 / CuSi3Mn1			
	W.Nr.	2.1461			
	F-nr	32			
SUITABLE FOR	Welding thin steel plates and or galvanized plates in the car industry and also for cladding CuMn, CuSiMn and CuZn alloys. Suitable for cladding cast iron and un- and low alloyed steels. Sislicon Alloy: 2.0220 - CuZn 5, 2.0230 - CuZn 10, 2.0240 - CuZn 15, 2.1322 - CuMg 0,4, 2.1323 - CuMg 0,7				
APPROVALS					
WELDING POSITIONS	PAPBPCPDPEPFPG				
TYPICAL CHEMICAL ANALYSIS OF THE FILLER METAL (%)	Si	Mn		Cu	
	2.95	0.9		Rem.	
MECHANICAL PROPERTIES	Heat Treatment	R _{P0,2} (MPa)	R _m (MPa)	A5 (%)	Hardness
	As Welded		350		80 HB
REDRYING	Not required				
GAS ACC. EN ISO 14175	I1, I3				



CEWELD CuSi3 Tig

CUSI3 TIG 1,6 X 1000MM

Packaging	KG/unit	EanCode
Tube	5	8720663408310

CUSI3 TIG 2,0 X 1000MM

Packaging	KG/unit	EanCode
Tube	5	8720663408327

CUSI3 TIG 2,4 X 1000MM

Packaging	KG/unit	EanCode
Tube	5	8720663408334

CUSI3 TIG 3,0 X 1000MM

Packaging	KG/unit	EanCode
Tube	5	8720663408341

CUSI3 TIG 3,2 X 1000MM

Packaging	KG/unit	EanCode
Tube	5	8720663408358

CUSI3 TIG 4,0 X 1000MM

Packaging	KG/unit	EanCode
Tube	5	8720663408365