



CEWELD MA 4115 Tig

TYPE Solid stainless 17% Chromium welding wire

APPLICATIONS Hardfacing shafts from stainless steel parts, molt repairs, rebuilding pump parts, thermal spray etc. Suitable for plating and joining equal and similar ferritic Cr-steels and cast steels. Proper weldings are subject to the recommended heat treatment. This welding wire is specially suitable for sealing surfaces on water-, steamand gas-valves, especially for sulphuric gases. The deposit is resistant to seawater, thin acids and scale resistant in air and oxidizing gases up to 950°C. The weld deposit can be tempered.

PROPRIÉTÉS Stainless steel alloy for joining and cladding 17% Chromium alloys and cladding components where heat and corrosion resistance simmlar to AISI 304 is required.The weld deposit can sustain working temperatures up to 450°C and will offer a high hardness and wear resistance.

CLASSIFICATION	AWS	A 5.9: ER430
	EN ISO	14343-A: W 17
	DIN	8555: TIG 6-GZ-200-PR
	W.Nr.	1.4115
	FM	5

CONVIENT POUR 1.4122 (G)X35CrMo17, Cast steels

AGRÉMENTS

POSITIONS DE SOUDAGE



**ANALYSE CHIMIQUE
TYPIQUE DU MÉTAL
D'APPORT (%)**

C	Si	Mn	Cr	Ni	Mo
0.1	0.5	0.6	16.5	0.5	0.5

PROPRIÉTÉS MÉCANIQUES

Heat Treatment	R _{p0,2} (MPa)	R _m (MPa)	A ₅ (%)	Hardness
As Welded	>300	>450	>20	45 HRc

ETUVAGE Not required

GAS ACC. EN ISO 14175 I1



CEWELD MA 4115 Tig

MA 4115 TIG 1,6 X 1000MM	Packaging	KG/unit	EanCode
	Tube	5	8720663403261
MA 4115 TIG 2,0 X 1000MM	Packaging	KG/unit	EanCode
	Tube	5	8720663403278
MA 4115 TIG 3,0 X 1000MM	Packaging	KG/unit	EanCode
	Tube	5	8720663403285