


CEWELD OA WC2 Fe

TYPE	Iron based flux cored wire for hardfacing containing a high amount of fused tungsten carbides.				
APPLICATIONS	This fused tungsten carbide based alloy provides an excellent resistance against extreme abrasion wear. OA WC2-Fe can be applied on most type of steels except on cast iron or Mn-steel. This alloy is the most wear resistant type in almost any hardfacing application.				
PROPRIÉTÉS	2400 HV Iron and Tungsten based hardfacing alloy containing 52-58% (depending on wire diameter) tungsten carbides. OA WC2-Fe has good welding characteristics. Multi-layer deposits are not recommended due to the extreme high hardness. Fused tungsten carbide will guaranty a long life for several wear applications. Best to be used without gas protection (self shielded).				
CLASSIFICATION	EN ISO	14700: T Fe20			
	DIN	8555: MF 21-GF-65-GZ			
CONVIENT POUR	Rebuilding of stabilisers and other oilfield tools where maximum protection against abrasion is required. Also for augers, impellers, mixer plates in the brick and clay industry and on decanter screws or hardfacing deep drilling equipment.				
AGRÉMENTS					
POSITIONS DE SOUDAGE	PAPBPC				
ANALYSE CHIMIQUE TYPIQUE DU MÉTAL DE SOUDURE (%)	WSC 56				
PROPRIÉTÉS MÉCANIQUES	Heat Treatment	R _{P0,2} (MPa)	R _m (MPa)	A5 (%)	Hardness
	As Welded				2400 HV
ETUVAGE	140°C / 24 hr				
HARDNESS	matrix: 65-67HRC, Carbides: 2400HV				
GAS ACC. EN ISO 14175					



CEWELD OA WC2 Fe

OA WC2 FE 1,6MM

Packaging	KG/unit	EanCode
BS-300	15	8720663403834

OA WC2 FE 2,4MM

Packaging	KG/unit	EanCode
BS-300	15	8720663403858