




CEWELD E AlSi 5

TYPE	Coated electrode for rapidly joining aluminum alloys and aluminium cast alloys..	
APPLICATIONS	Stick electrode for welding Aluminium alloys with maximum 2% alloying elements and for aluminium alloys containing up to 7% Si.	
PROPRIÉTÉS	Very good weldability with good penetration and porosity free deposit, Unique self lifting slag and improved coating against moisture pick up. (after anodizing the welding will appear as a dark grey color)	
CLASSIFICATION	AWS	A 5.3: E 4043
	EN ISO	18273: E AlSi5(A)
	W.Nr.	3.2245
	F-nr	23
	FM	23
CONVIENT POUR	AlSi alloys with max. 7% Silicium, AlMg Alloys with max. 3% Magnesium, Mat.n: 3.2151, 3.3206, 3.3210, 3.3211, 3.2305, 3.2315, 3.2341, 3.2371, 3.4335 AlMgSi 0.5, AlMgSi 0.7, AlMgSi 1, AlMg1SiCu, AlSi7Mg0,3, G.AlSi5Mg, G.AlSi6Cu4, AlMgSi, AlZn4,5Mg1 Iso.n: 6060, 6005A, 6082, 6061, 4210, 4500, 6060, 7072	

AGRÉMENTS

POSITIONS DE SOUDAGE



ANALYSE CHIMIQUE TYPIQUE DU MÉTAL DE SOUDURE (%)

Si	Mn	Ti	Fe	Cu	Mg	Al
5	0.02	0.2	0.2	0.3	0.05	Rem.

PROPRIÉTÉS MÉCANIQUES

Heat Treatment	R _{P0,2} (MPa)	R _m (MPa)	A5 (%)	Hardness
As Welded	100	150	14	60 HB

ETUVAGE

Not required

GAS ACC. EN ISO 14175



CEWELD E ALSi 5

E ALSi 5 2,5 X 350MM

Packaging	KG/unit	EanCode
Can	2	8720663406712

E ALSi 5 3,2 X 350MM

Packaging	KG/unit	EanCode
Can	2	8720663406729

E ALSi 5 4,0 X 350MM

Packaging	KG/unit	EanCode
Can	2	8720663406736