



CEWELD AA NiCrSiB

TYPE	High-alloyed tubular wire on a Ni-Cr-Si-B basis for high wear protection in several applications.	
TOEPASSINGEN	The characteristics of the deposit are comparable with cobalt-base alloys but with higher hardness, excellent corrosion resistance, heat resistance and thermal shock constancy.	
EIGENSCHAPPEN	Very good corrosion resistance combined with high hardness even at higher temperatures. Excellent weldability and often used as economical alternative for „stellite“	
CLASSIFICATIE	EN ISO	14700: T Ni1

GESCHIKT VOOR rotary seal rings, pumps, sleeves, grinder parts, chemical and glas industry.

GOEDKEURINGEN

LASPOSITIES



TYPICAL CHEMICAL ANALYSIS OF WELD METAL (%)

C	Si	Mn	Cr	Ni	Fe	B
0.75	4.2	0.5	13.5	80	3	3

MECHANISCHE WAARDEN

Heat Treatment	R _{P0,2} (MPa)	R _m (MPa)	A5 (%)	Hardness
As Welded				58 HRc

HERDROGEN 140°C / 24 hr

GAS ACC. EN ISO 14175 I1



CEWELD AA NiCrSiB

AA NICRSIB 1,2MM

Packaging	KG/unit	EanCode
BS-300	15	8720663403322