

# CEWELD 2594 Super Duplex

**TYPE** 2594 Super Duplex stainless steel Mig/Mag GMAW welding wire for Zeron 100, Uranus 76, SAF 2507 and similar alloys

**TOEPASSINGEN** Welding austenitic-ferritic, stainless alloys of the 25% Cr, 7% Ni, 4% Mo, low C types. Welding wrought, forged or cast super duplex stainless steels for service in the as-welded Condition. Heterogeneous welding between super duplex stainless steels and dissimilar welds between other stainless and mild or low alloyed steels. The alloy is widely used in applications in which corrosion resistance is of the utmost importance. The pulp & paper industry, offshore and gas industry are areas of interest.

**EIGENSCHAPPEN** CEWELD 2594 has high intergranular-corrosion, pitting and stress-corrosion resistance with exceptional mechanical strength properties.

**CLASSIFICATIE**

|        |                       |
|--------|-----------------------|
| AWS    | A 5.9: ER2594         |
| EN ISO | 14343-A: G 25 9 4 N L |
| W.Nr.  | 1.4410                |
| F-nr   | 6                     |
| FM     | 5                     |

**GESCHIKT VOOR** **ISO 15608: 10.2-10.3 Austenitic > 24 % Cr ≤ 4% Ni, DUPLEX 2594, 25%Cr 9%Ni 4%Mo**  
1.4410, 1.4467, 1.4468, 1.4501, 1.4507, 1.4508, 1.4515, 1.4517, 1.4569  
X2 CrNiMoCuN 25-6-3, X2 CrNiMoN 25-7-4, GX2 CrNiMoN 25-6-3, GX2 CrNiMoCuN 26-6-3, GX2 CrNiMoCuN 25-6-3-3, X2 CrNiMoCuWN 25-7-4, X2CrMnNiMoN26-5-4, X 2 CrNiMoN 26 7 4, GX2CrNiMoCuWN25-8-4  
UNS S32520, S32550, S32750, S39274, S39277, S39553, S32760, J93380, J93404  
Ferrallium 255, SAF 2507, ZERON 100, UR 76 N, SM22Cr, SAF 2507, Alloy 2507, Alloy 2594, Super Duplex, Uranus® 47N

**GOEDKEURINGEN** CE

**LASPOSITIES**



**TYPICAL CHEMICAL ANALYSIS OF THE FILLER METAL (%)**


| C    | Si  | Mn  | Cr | Ni | Mo  | N   | W   |
|------|-----|-----|----|----|-----|-----|-----|
| 0.02 | 0.6 | 1.2 | 25 | 9  | 3.5 | 0.2 | 0.4 |

**MECHANISCHE WAARDEN**

| Heat Treatment | R <sub>p0.2</sub> (MPa) | R <sub>m</sub> (MPa) | A <sub>5</sub> (%) | Impact Energy (J) ISO-V |       | Hardness |
|----------------|-------------------------|----------------------|--------------------|-------------------------|-------|----------|
|                |                         |                      |                    | -20°C                   | -40°C |          |
| As Welded      | 700                     | 900                  | 27                 | 65                      | 55    | HRc      |

**HERDROGEN** Not required

**GAS ACC. EN ISO 14175** M13, M12



# CEWELD 2594 Super Duplex

|                         |           |         |               |
|-------------------------|-----------|---------|---------------|
| 2594 SUPER DUPLEX 0,8MM | Packaging | KG/unit | EanCode       |
|                         | BS-300    | 15      | 8720663414694 |
| 2594 SUPER DUPLEX 1,0MM | Packaging | KG/unit | EanCode       |
|                         | BS-300    | 15      | 8720663414700 |
| 2594 SUPER DUPLEX 1,2MM | Packaging | KG/unit | EanCode       |
|                         | BS-300    | 15      | 8720663414717 |