



CEWELD ER 80S-B2 Tig

TYPE	Copper coated welding wire for welding creep resistant ferritic steels.					
TOEPASSINGEN	Is a Filler metal for high temperature creep resistant 1.25%Cr 0.5%Mo ferritic steel. These steels are used for creep resisting applications up to ~550 °C. Typical applications in power generation plant include steam piping, turbines and boilers; the alloy also finds applications in the chemical and petro-chemical industries.					
EIGENSCHAPPEN	The CEWELD® ER 80S-B2 Tig has low levels of tramp elements (e.g. Sn, As, Sb and P) providing a low Bruscato Factor(X< 10 ppm)for temper embrittlement resistant applications.					
CLASSIFICATIE	AWS	A 5.28: ER 80S-B2				
	EN ISO	21952-B: W 1CM				
	F-nr	6				
	FM	3				
GESCHIKT VOOR	For matching 1.25%Cr 0.5%Mo creep resisting ferritic steels. 13CrMo4-5, 16CrMo4-4, GS-17CrMo5-5 ASTM: A182 grades F11/F12, A199/A200 T11, A217 grades WC6/WC11, A234 grades WP11/WP12, A335 grades P11/P12, A387 grades 11/12					
GOEDKEURINGEN	CE					
LASPOSITIES	 PA  PB  PC  PD  PE  PF  PG					
TYPICAL CHEMICAL ANALYSIS OF THE FILLER METAL (%)	C	Si	Mn	Cr	Mo	
	0.09	0.6	0.6	1.3	0.5	
MECHANISCHE WAARDEN	Heat Treatment	R _{P0,2} (MPa)	R _m (MPa)	A ₅ (%)	Impact Energy (J) ISO-V	Hardness
	620°C±15°C 1h	560	660	24	RT	
					200	HRc
HERDROGEN	Not required					
GAS ACC. EN ISO 14175	I1					



CEWELD ER 80S-B2 Tig

ER 80S-B2 TIG 1,6MM

Packaging	KG/unit	EanCode
Tube	5	8720663417466

ER 80S-B2 TIG 2,0 X
1000MM

Packaging	KG/unit	EanCode
Tube	5	8720663417480

ER 80S-B2 TIG 2,4 X
1000MM

Packaging	KG/unit	EanCode
Tube	5	8720663417497

ER 80S-B2 TIG 3,2 X
1000MM

Packaging	KG/unit	EanCode
Tube	5	8720663417527